

University of Nebraska at Omaha DigitalCommons@UNO

Chemistry Faculty Publications

Department of Chemistry

3-2017

Crystal structure of Li3Ga(BO3)2

Robert W. Smith University of Nebraska at Omaha, robertsmith@unomaha.edu

Darien Holman University of Nebraska at Omaha

Eric M. Villa Creighton University

Follow this and additional works at: https://digitalcommons.unomaha.edu/chemfacpub

Part of the Chemistry Commons

Please take our feedback survey at: https://unomaha.az1.qualtrics.com/jfe/form/ SV_8cchtFmpDyGfBLE

Recommended Citation

Smith, Robert W.; Holman, Darien; and Villa, Eric M., "Crystal structure of Li3Ga(BO3)2" (2017). *Chemistry Faculty Publications*. 34.

https://digitalcommons.unomaha.edu/chemfacpub/34

This Article is brought to you for free and open access by the Department of Chemistry at DigitalCommons@UNO. It has been accepted for inclusion in Chemistry Faculty Publications by an authorized administrator of DigitalCommons@UNO. For more information, please contact unodigitalcommons@unomaha.edu.



research communications



Received 29 December 2016 Accepted 21 February 2017

Edited by M. Weil, Vienna University of Technology, Austria

Keywords: crystal structure; crystal diffraction; gallium; borate.

CCDC reference: 1534100

Supporting information: this article has supporting information at journals.iucr.org/e



OPEN d ACCESS

Crystal structure of Li₃Ga(BO₃)₂

Robert W. Smith,^a* Darien Holman^a and Eric M. Villa^b

^aDepartment of Chemistry, University of Nebraska at Omaha, 6001 Dodge Street, Omaha, Nebraska 68182, USA, and ^bDepartment of Chemistry, Creighton University, 2500 California Plaza, Omaha, Nebraska 68178, USA. *Correspondence e-mail: robertsmith@unomaha.edu

The crystal structure of trilithium gallium bis(orthoborate), $Li_3Ga(BO_3)_2$, is isotypic with $Li_3Al(BO_3)_2$ in a triclinic cell in space-group type $P\overline{1}$. The three Li and the unique Ga atom are coordinated by four O atoms each in tetrahedra, and the two B atoms are coordinated by three O atoms in orthoborate triangles. Chains with composition $[Ga_2(BO_3)_4]^{6-}$ extend along the *a* axis. The Li atoms interleave these chains in tetrahedral interstices. A comparison is made between the structure model of the title compound and that of a previously reported model for a compound with the same composition [Abdullaev & Mamedov (1972). *Zh. Strukt. Khim.* **13**, 943–946.]

1. Chemical context

We are examining the alkali metal/gallium/borate phase diagrams, investigations of which have revealed to date, among others, the homologous series $A_2Ga_2O(BO_3)_2$, in which A = Na, K, Rb, and Cs (Corbel & Leblanc, 2000; Smith, 1995; Smith *et al.*, 1997,2008, respectively) and the homologous series $A_3Ga(BO_3)_2$, in which A = Li, Na, K, Rb, and Cs. We report herein the crystal structure of the lithium analog (Fig. 1) of the latter series, which is the only one which melts congruently, which has a unique structure among the series, and which is isotypic with $Li_3Al(BO_3)_2$ (He *et al.*, 2002); the other analogs have yet to be crystallized in the form of single crystals, but are structurally distinct from the lithium analog and isotypic with each other based on their powder X-ray diffraction patterns.

A crystal structure for this compound was previously reported by Abdullaev & Mamedov (1972) in the same triclinic space-group type $P\overline{1}$, and with the same galliumborate polyhedral pattern but with important differences with the structure reported herein, to wit: slightly different cell parameters and a different reduced cell, a significantly smaller cell volume (i.e., 3% smaller), less regular bond-valence sums (BVS), greater deviations from expected interatomic distances, and irregular, five- and six-coordinate lithiumcentered polyhedra. Table 1 compares interatomic distances from the structure reported by Addullaev & Mamedov (1972) and this report, with expected distances using Shannon's radii (Shannon, 1976); it also lists bond-valence sums for each structure. We have considered as bonds all Li-O distances under 3 Å from the 1972 report because doing so produces more reasonable BVS values, thus rendering some of the lithium atoms as being five- or six-coordinate in the previous structure report. It should be noted that the authors, however, reported all lithium atoms as tetrahedrally coordinated. The present structure model clearly differs from the 1972 structure

Structure model	Abdullaev & Mamedov (1972)	Current work	Shannon (1976)
Reduced cell (Å, °)	4.90 (2) 6.23 (3) 7.78 (5) 72.9 (5) 90.0 (5) 90.0 (5)	4.8731 (3) 6.2429 (4) 8.0130 (5) 73.346 (6) 89.701 (5) 89.698 (5)	
Range of interatomic	c distances (Å)		
Li–O	2.28 ± 0.41	1.965 ± 0.054	1.97
Ga-O	2.07 ± 0.43	1.847 ± 0.021	1.85
B-O	1.31±0.13	1.384 ± 0.038	1.39
Bond-valence-sum va	alues and coordination numbers (in brackets)		
Li (1, 2 & 3)	1.14 [4 + 1], 1.01 [4], 1.00 [6]	1.07 [4], 1.03 [4], 1.05 [4]	
Ga (1)	2.38 [4]	2.92 [4]	
B (1 & 2)	3.17 [3], 3.06 [3]	2.91 [3], 2.91 [3]	

 Table 1

 Comparison of the two structures with composition Li₃Ga(BO₃)₂.

model and hence indicates a second possible modification for this composition. Whether a polymorphic relation exists between the two phases remains unknown and needs additional proof by using complementary methods such as thermal analysis.



Figure 1

A projection of the crystal structure of $Li_3Ga(BO_3)_2$ along the *a* axis. Infinite $[Ga_2(BO_3)_4]^{6-}$ chains are linked together by sheets of Li atoms in tetrahedral voids. GaO_4 tetrahedra are light green, LiO_4 tetrahedra are light gray, and BO_3 triangles are blue–grey. Corner O atoms have been omitted for clarity.

2. Structural commentary

The crystal structure of the title compound consists of lithiumand gallium-centered tetrahedra and boron-centered triangles, all of which share oxygen vertices (Fig.1). Each GaO₄ tetrahedron is linked to four BO₃ triangles and six LiO₄ tetrahedra. The gallium-centered tetrahedra and boron-centered triangles adjoin through shared vertices to form infinite chains of composition $[Ga_2(BO_3)_4]^{6-}$, with the chains extending parallel to the *a* axis; lithium cations interleave the chains in tetrahedral interstices. Fig. 2 shows a comparison of the galliumborate chains in both the previously reported structure (Abdullaev & Mamedov, 1972) and the structure presented here. The two exhibit the same connectivity but have sizeable





A comparison of the infinite $[Ga_2(BO_3)_4]^{6-}$ chains in the structures of $Li_3Ga(BO_3)_2$ with respect to the model by Abdullaev & Mamedov (1972) (top) and the structure model presented in this manuscript. The connectivity of these two chains are the same but there are important differences in the actual bonding. In our structure model, these chains run down the *c* axis. Here the GaO₄ tetrahedra are light green and the BO₃ triangles are blue–grey (which are shown in light blue–grey in the 1972 structure). Corner O atoms have been omitted for clarity.

research communications



Figure 3

The asymmetric unit of the title structure with atom labelling. Displacement ellipsoids are drawn at the 75% probability level.

differences in bond lengths, bond angles and bond-valencesum values (see Table 1). Averaged interatomic distances for the title structure are consistent with those determined from the ionic radii reported by Shannon (1976), *viz.* 1.97 (5), 1.85 (2), and 1.39 (4) Å for the experimentally determined Li–O, Ga–O, and B–O distances, respectively. We also calculated the bond-valence-um values for each element using the values provided by Brese & O'Keeffe (1991). The results (Table 1) are in good agreement with the expected values of 1, 3, 3 and 2 for Li, Ga, B and O atoms, respectively.

Lastly, Fig. 3 displays the anisotropic displacement parameters of the atoms within the asymmetric unit of the title structure.

3. Synthesis and crystallization

Powder samples were made by solid-state reactions starting with stoichiometric proportions of lithium nitrate, gallium(III) nitrate, and boric acid. We first ground the starting materials and fired them in an alumina crucible at 573 K for two h to decompose them to finely divided oxides, after which we progressively heated the samples to 973 K at 50 to 100 K and 24-hour increments, grinding the samples between each successive heat treatment. Samples were single-phase as revealed by powder X-ray diffraction.

Single crystals were grown from the melt. About 500 mg of sample were placed in a platinum dish, heated to 1033 K in a box oven, slow-cooled at 10 K h^{-1} to about 470 K, and then air-quenched. Several small, clear, colorless crystals were physically removed from the platinum crucible and mounted on a goniometer for a preliminary scan in order to find one of suitable quality.

Table 2 Experimental details.	
Crystal data	
Chemical formula	$Li_3Ga(BO_3)_2$
M _r	208.16
Crystal system, space group	Triclinic, $P\overline{1}$
Temperature (K)	293
a, b, c (Å)	4.8731 (3), 6.2429 (4), 8.0130 (5)
α, β, γ (°)	73.346 (6), 89.701 (5), 89.698 (5)
$V(\dot{A}^3)$	233.54 (3)
Z	2
Radiation type	Μο Κα
$\mu \text{ (mm}^{-1})$	5.84
Crystal size (mm)	$0.09 \times 0.03 \times 0.01$
Data collection	
Diffractometer	Rigaku SCX mini diffractometer
Absorption correction	Multi-scan (<i>CrysAlis PRO</i> ; Rigaku Oxford Diffraction, 2015)
T_{\min}, T_{\max}	0.785, 1.000
No. of measured, independent and observed $[I > 2\sigma(I)]$ reflections	2936, 1397, 1265
R _{int}	0.029
$(\sin \theta / \lambda)_{\rm max} ({\rm \AA}^{-1})$	0.714
Refinement	
$R[F^2 > 2\sigma(F^2)], wR(F^2), S$	0.028, 0.067, 1.09
No. of reflections	1397
No. of parameters	109
$\Delta \rho_{\rm max}$, $\Delta \rho_{\rm min}$ (e Å ⁻³)	1.04, -0.76

Computer programs: CrysAlis PRO (Rigaku Oxford Diffraction, 2015), SHELXT (Sheldrick, 2015a), SHELXL2014 (Sheldrick, 2015b) and OLEX2 (Dolomanov et al., 2009).

4. Refinement

Crystal data, data collection and structure refinement details are summarized in Table 2.

Acknowledgements

EMV would like to acknowledge Creighton University for financial support.

References

- Abdullaev, G. K. & Mamedov, Kh. S. (1972). Zh. Strukt. Khim. 13, 943–946.
- Brese, N. E. & O'Keeffe, M. (1991). Acta Cryst. B47, 192–197.
- Corbel, G. & Leblanc, M. (2000). J. Solid State Chem. **154**, 344–349. Dolomanov, O. V., Bourhis, L. J., Gildea, R. J., Howard, J. A. K. &
- Puschmann, H. (2009). J. Appl. Cryst. 42, 339-341.
- He, M., Chen, X. L., Gramlich, V., Baerlocher, Ch., Zhou, T. & Hu, B. Q. (2002). J. Solid State Chem. 163, 369–376.
- Rigaku Oxford Diffraction (2015). CrysAlis PRO. Rigaku Oxford Diffraction, Yarnton, Oxfordshire, England.
- Shannon, R. D. (1976). Acta Cryst. A32, 751-767.
- Sheldrick, G. M. (2015a). Acta Cryst. A71, 3-8.
- Sheldrick, G. M. (2015b). Acta Cryst. C71, 3-8.
- Smith, R. W. (1995). Acta Cryst. C51, 547-549.
- Smith, R. W., Hu, C. & DeSpain, C. D. (2008). Acta Cryst. E64, i23.
- Smith, R. W., Kennard, M. A. & Dudik, M. J. (1997). Mater. Res. Bull. 32, 649–656.

supporting information

Acta Cryst. (2017). E73, 456-458 [https://doi.org/10.1107/S205698901700295X]

Crystal structure of Li₃Ga(BO₃)₂

Robert W. Smith, Darien Holman and Eric M. Villa

Computing details

Data collection: *CrysAlis PRO* (Rigaku Oxford Diffraction, 2015); cell refinement: *CrysAlis PRO* (Rigaku Oxford Diffraction, 2015); data reduction: *CrysAlis PRO* (Rigaku Oxford Diffraction, 2015); program(s) used to solve structure: SHELXT (Sheldrick, 2015a); program(s) used to refine structure: *SHELXL2014* (Sheldrick, 2015b); molecular graphics: *OLEX2* (Dolomanov *et al.*, 2009); software used to prepare material for publication: *OLEX2* (Dolomanov *et al.*, 2009).

Z = 2

F(000) = 196

 $\theta = 2.7 - 32.5^{\circ}$

 $\mu = 5.84 \text{ mm}^{-1}$

T = 293 K

 $D_{\rm x} = 2.960 {\rm Mg} {\rm m}^{-3}$

Mo *K* α radiation, $\lambda = 0.71073$ Å

Plate, clear light colourless

 $0.09 \times 0.03 \times 0.01 \text{ mm}$

Cell parameters from 1687 reflections

Trilithium gallium bis(orthoborate)

Crystal data

Li₃Ga(BO₃)₂ $M_r = 208.16$ Triclinic, $P\overline{1}$ a = 4.8731 (3) Å b = 6.2429 (4) Å c = 8.0130 (5) Å a = 73.346 (6)° $\beta = 89.701$ (5)° $\gamma = 89.698$ (5)° V = 233.54 (3) Å³

Data collection

Rigaku SCX mini	$T_{\min} = 0.785, T_{\max} = 1.000$
diffractometer	2936 measured reflections
Radiation source: fine-focus sealed X-ray tube,	1397 independent reflections
Enhance (Mo) X-ray Source	1265 reflections with $I > 2\sigma(I)$
Graphite monochromator	$R_{\rm int} = 0.029$
ω scans	$\theta_{\rm max} = 30.5^{\circ}, \theta_{\rm min} = 2.7^{\circ}$
Absorption correction: multi-scan	$h = -6 \rightarrow 6$
(CrysAlis PRO; Rigaku Oxford Diffraction,	$k = -8 \rightarrow 8$
2015)	$l = -11 \rightarrow 11$

Refinement

Refinement on F^2 0 restraintsLeast-squares matrix: fullPrimary atom site location: dual $R[F^2 > 2\sigma(F^2)] = 0.028$ $w = 1/[\sigma^2(F_o^2) + (0.0282P)^2 + 0.1042P]$ $wR(F^2) = 0.067$ where $P = (F_o^2 + 2F_c^2)/3$ S = 1.09 $(\Delta/\sigma)_{max} < 0.001$ 1397 reflections $\Delta\rho_{max} = 1.04$ e Å⁻³109 parameters $\Delta\rho_{min} = -0.76$ e Å⁻³

Special details

Geometry. All esds (except the esd in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell esds are taken into account individually in the estimation of esds in distances, angles and torsion angles; correlations between esds in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell esds is used for estimating esds involving l.s. planes.

Refinement. Crystals of Li₃Ga(BO₃)₂ were mounted on MiTeGen Microloop with non-drying immersion oil. The crystal was then optically aligned on the Rigaku SCX-Mini diffractometer using a digital camera. Initial matrix images were collected to determine the unit cell, validity and proper exposure time. Three hemispheres (where φ = 0.0, 120.0 and 240.0) of data were collected with each consisting 180 images each with 1.00° widths and a 1.00° step. The structure of Li₃Ga(BO₃)₂ was refined using SHELXT (Sheldrick, 2015) Intrinsic Phasing and SHELXL (Sheldrick, 2015). Olex2 (Dolomanov *et al.*, 2009) was used as a graphical interface. Images of the above compound were made using CrystalMaker for Windows, version 9.2.8. The refinement proceeded without any incidents and without any need for modelling disorder or twinning or any constraints or restraints.

Refinement of the structure was based on F^2 against all reflections. The R-factor R is based on $F^2>2?(F^2)$, but is not relevant to the choice of reflections for refinement; whereas the weighted R-factor wR and goodness of fit S are based on F^2 . The maximum electron denisty is 1.035 and is located 1.629 Å from Li(2), 1.960 Å from Li(1) and 2.169 Å from a different Li(1), which leads to nothing reasonable. All other maximum peaks are under 0.600.

	x	У	Ζ	$U_{ m iso}$ */ $U_{ m eq}$	
Ga1	0.65937 (6)	0.22951 (4)	0.60906 (4)	0.00968 (10)	
B1	0.1691 (6)	0.0135 (5)	0.7454 (4)	0.0088 (5)	
B2	0.6631 (6)	0.5014 (5)	0.2489 (4)	0.0094 (5)	
01	0.3037 (4)	0.1391 (3)	0.5958 (2)	0.0116 (4)	
O2	-0.1202 (4)	-0.0028 (3)	0.7317 (2)	0.0101 (4)	
03	0.2978 (4)	-0.0830 (3)	0.8955 (2)	0.0109 (4)	
04	0.7953 (4)	0.3547 (3)	0.3900 (2)	0.0117 (4)	
05	0.3833 (4)	0.5529 (3)	0.2727 (2)	0.0100 (4)	
06	0.7921 (4)	0.5853 (3)	0.0967 (2)	0.0120 (4)	
Li1	0.1828 (10)	-0.3717 (8)	1.0414 (6)	0.0154 (10)	
Li2	1.1645 (10)	0.2738 (8)	0.3670 (6)	0.0143 (9)	
Li3	0.6839 (10)	0.8785 (8)	-0.0399 (6)	0.0159 (10)	

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters $(Å^2)$

Atomic displacement parameters $(Å^2)$

					1.2	
	U^{Π}	U^{22}	U^{33}	U^{12}	U^{13}	U^{23}
Gal	0.00877 (15)	0.01034 (15)	0.00789 (15)	-0.00023 (10)	0.00130 (10)	0.00064 (10)
B1	0.0103 (13)	0.0052 (11)	0.0106 (12)	0.0008 (9)	0.0021 (10)	-0.0018 (10)
B2	0.0091 (13)	0.0088 (12)	0.0095 (12)	-0.0013 (10)	0.0002 (10)	-0.0013 (10)
O1	0.0098 (9)	0.0134 (9)	0.0090 (8)	-0.0028 (7)	0.0011 (7)	0.0012 (7)
02	0.0068 (8)	0.0105 (8)	0.0098 (8)	0.0013 (6)	0.0002 (7)	0.0020 (7)
O3	0.0107 (9)	0.0104 (8)	0.0094 (8)	-0.0007(7)	-0.0018 (7)	0.0008 (7)
O4	0.0110 (9)	0.0138 (9)	0.0066 (8)	0.0017 (7)	0.0012 (7)	0.0030 (7)
05	0.0088 (9)	0.0102 (8)	0.0104 (8)	0.0008 (7)	0.0013 (7)	-0.0017 (7)
06	0.0136 (9)	0.0114 (9)	0.0088 (8)	-0.0001 (7)	0.0029 (7)	0.0005 (7)
Li1	0.019 (2)	0.013 (2)	0.013 (2)	-0.0038 (18)	0.0013 (18)	-0.0023 (18)
Li2	0.012 (2)	0.014 (2)	0.013 (2)	-0.0009 (17)	0.0008 (17)	0.0009 (17)
Li3	0.013 (2)	0.017 (2)	0.015 (2)	-0.0014 (18)	0.0000 (18)	-0.0016 (18)

Geometric parameters (Å, °)

Ga1—O1	1.8385 (18)	B1—O2	1.421 (3)
Ga1—O2 ⁱ	1.8440 (18)	B1—O3	1.339 (3)
Ga1—O4	1.8272 (18)	B2—O4	1.393 (3)
Ga1—O5 ⁱⁱ	1.8759 (18)	B2—O5	1.423 (3)
B1—O1	1.393 (3)	B2—O6	1.336 (3)
O1—Ga1—O2 ⁱ	111.84 (8)	Li1 ^{xii} —Li1—Li3 ^{vii}	149.2 (3)
O1—Ga1—O5 ⁱⁱ	102.08 (8)	Li1 ^{xii} —Li1—Li3 ^{ix}	72.2 (2)
O1—Ga1—Li1 ⁱⁱⁱ	116.15 (10)	Li2 ^{ix} —Li1—Ga1 ⁱⁱⁱ	63.94 (14)
O1—Ga1—Li2 ^{iv}	124.51 (10)	Li2 ^{ix} —Li1—Li3 ^{viii}	60.89 (16)
O1—Ga1—Li2 ^v	35.98 (10)	Li2 ^{ix} —Li1—Li3 ⁱⁱ	120.2 (2)
O1—Ga1—Li2 ^{vi}	86.55 (10)	Li3 ⁱⁱ —Li1—Ga1 ⁱⁱⁱ	56.40 (12)
O1—Ga1—Li2	133.42 (11)	Li3 ^{vii} —Li1—Ga1 ⁱⁱⁱ	74.07 (15)
O1—Ga1—Li3 ^{vii}	86.54 (11)	Li3 ^{viii} —Li1—Ga1 ⁱⁱⁱ	117.59 (17)
O2 ⁱ —Ga1—O5 ⁱⁱ	111.37 (8)	Li3 ^{ix} —Li1—Ga1 ⁱⁱⁱ	97.77 (17)
O2 ⁱ —Ga1—Li1 ⁱⁱⁱ	76.62 (10)	Li3 ^{vii} —Li1—Li2 ^{ix}	117.0 (2)
$O2^{i}$ —Ga1—Li2 ^{iv}	115.22 (10)	$Li3^{ix}$ — $Li1$ — $Li2^{ix}$	114.0 (2)
Ω^{2i} -Ga1-Li2 ^v	135.30 (11)	$Li3^{ii}$ — $Li1$ — $Li3^{viii}$	156.5 (2)
Ω^{2i} Gal Li2 ^{vi}	37.59 (10)		107.55 (19)
$O2^{i}$ —Gal—Li2	77.78 (10)	$Li3^{ix}$ — $Li1$ — $Li3^{viii}$	129.60 (18)
Ω^{2i} Gal Li ^{3vii}	39.95 (11)	$Li3^{vii}$ — $Li1$ — $Li3^{ii}$	49.58 (19)
O4-Ga1-O1	109.76 (8)	$Li3^{ix}$ — $Li1$ — $Li3^{ii}$	73.05 (19)
$O4-Ga1-O2^{i}$	110.94 (8)	$Li3^{ix}$ — $Li1$ — $Li3^{vii}$	116.4 (2)
$O4-Ga1-O5^{ii}$	110.54 (8)	Ga1—Li2—Ga1 ^{vi}	105.15 (13)
$O4-Ga1-Li1^{iii}$	126.18 (10)	Gal ⁱ —Li2—Gal ^{iv}	70.59 (10)
O4-Ga1-Li2	34.37 (10)	Ga1—Li2—Ga1 ^{iv}	95.24 (13)
$O4$ — $Ga1$ — $Li2^{vi}$	96.01 (11)	Gal ⁱ —Li2—Gal	104.73 (14)
O4—Ga1—Li2 ^v	74.92 (11)	$Ga1^{i}$ —Li2—Ga1 ^{vi}	81.11 (11)
O4—Ga1—Li2 ^{iv}	78.99 (10)	$Ga1^{vi}$ —Li2—Ga1 ^{iv}	148.57 (16)
04—Ga1—Li3 ^{vii}	150.82 (11)	$Ga1-Li2-Li3^{xiii}$	135.80 (19)
$O5^{ii}$ —Ga1—Li1 ⁱⁱⁱ	34.75 (10)	$Ga1^{i}$ —Li2—Li3 ^{xiii}	110.84 (17)
$O5^{ii}$ —Ga1—Li2 ^{iv}	33.37 (10)	$B1^{\text{viii}}$ $Li2$ $Ga1^{\text{i}}$	136.51 (18)
$O5^{ii}$ —Ga1—Li2 ^v	106.86 (11)	$B1^{viii}$ —Li2—Ga1 ^{vi}	57.25 (11)
$O5^{ii}$ —Ga1—Li2 ^{vi}	146.78 (10)	$B1^{viii}$ —Li2—Ga1 ^{iv}	152.84 (18)
$O5^{ii}$ —Ga1—Li2	116.90 (11)	$B1^{viii}$ —Li2—Ga1	77.51 (13)
$O5^{ii}$ —Ga1—Li3 ^{vii}	88.33 (11)	$B1^{viii}$ —Li2— $B2^{i}$	135.2 (2)
Li1 ⁱⁱⁱ —Ga1—Li2 ^{iv}	52.55 (11)	$B1^{viii}$ _Li2_Li1 ^{xi}	97.11 (18)
$Li2^{v}$ —Ga1—Li1 ⁱⁱⁱ	137.36 (13)	$B1^{viii}$ —Li2—Li3 ^{xiii}	58.70 (14)
Li2—Ga1—Li1 ⁱⁱⁱ	110.42 (13)	B2 ⁱ —Li2—Ga1	146.69 (19)
$Li2^{vi}$ —Ga1—Li1 ⁱⁱⁱ	112.82 (12)	$B2^{i}$ —Li2—Ga1 ^{vi}	100.55 (15)
Li2 ^v —Ga1—Li2	104.73 (14)	B2 ⁱ —Li2—Ga1 ⁱ	58.67 (11)
Li2—Ga1—Li2 ^{vi}	74.85 (13)	$B2^{i}$ —Li2—Ga1 ^{iv}	53.11 (10)
$Li2^{vi}$ —Ga1—Li2 ^{iv}	148.57 (16)	$B2^{i}$ —Li2—Li1 ^{xi}	59.61 (14)
$Li2^{v}$ —Ga1— $Li2^{iv}$	109.41 (10)	$B2^{i}$ —Li2—Li3 ^{xiii}	76.46 (16)
$Li2^{v}$ —Ga1— $Li2^{vi}$	98.89 (11)	$O1^{i}$ —Li2—Ga1 ^{vi}	72.19 (15)
Li2—Ga1—Li2 ^{iv}	84.76 (13)	$O1^{i}$ —Li2—Ga1	75.30 (16)
	()		

Li3 ^{vii} —Ga1—Li1 ⁱⁱⁱ	59.79 (12)	O1 ⁱ —Li2—Ga1 ^{iv}	90.70 (18)
Li3 ^{vii} —Ga1—Li2 ^{vi}	59.91 (13)	O1 ⁱ —Li2—Ga1 ⁱ	34.43 (10)
Li3 ^{vii} —Ga1—Li2 ^v	121.95 (13)	O1 ⁱ —Li2—B1 ^{viii}	112.1 (2)
Li3 ^{vii} —Ga1—Li2	117.45 (13)	$O1^{i}$ —Li2—B2 ⁱ	93.10 (19)
Li3 ^{vii} —Ga1—Li2 ^{iv}	112.26 (13)	O1 ⁱ —Li2—O2 ^{viii}	102.8 (2)
O1—B1—O2	115.8 (2)	$O1^{i}$ —Li2— $O5^{i}$	105.5 (2)
O1—B1—Li2 ^{viii}	104.8 (2)	O1 ⁱ —Li2—Li1 ^{xi}	149.9 (3)
O1—B1—Li3 ⁱⁱ	113.6 (2)	O1 ⁱ —Li2—Li3 ^{xiii}	124.6 (2)
O2—B1—Li2 ^{viii}	47.04 (15)	O2 ^{viii} —Li2—Ga1 ^{vi}	32.82 (9)
O2—B1—Li3 ⁱⁱ	111.9 (2)	O2 ^{viii} —Li2—Ga1	102.44 (18)
O3—B1—O1	123.3 (2)	O2 ^{viii} —Li2—Ga1 ^{iv}	159.9 (2)
O3—B1—O2	120.9 (2)	O2 ^{viii} —Li2—Ga1 ⁱ	113.13 (19)
O3—B1—Li2 ^{viii}	113.91 (19)	$O2^{viii}$ —Li2—B1 ^{viii}	30.07 (10)
O3—B1—Li3 ⁱⁱ	42.00 (16)	$O2^{\text{viii}}$ —Li2—B2 ⁱ	110.6 (2)
$Li3^{ii}$ —B1— $Li2^{viii}$	141.61 (18)	$O2^{viii}$ —Li2—Li1 ^{xi}	99.0 (2)
O4—B2—O5	117.1 (2)	$O2^{\text{viii}}$ —Li2—Li3 ^{xiii}	39.36 (13)
O4—B2—Li1 ^{viii}	106.0 (2)	O4—Li2—Gal	33.11 (10)
$O4-B2-Li2^{v}$	88.65 (18)	$O4-Li2-Ga1^{vi}$	121.9 (2)
04—B2—Li3	149.2 (2)	$O4-Li2-Ga1^{i}$	131.9 (2)
O5—B2—Li1 ^{viii}	119.8 (2)	$O4-Li2-Ga1^{iv}$	87.97 (18)
$05-B2-Li2^{v}$	41.16 (15)	$O4-Li2-B1^{viii}$	71.58 (17)
O5—B2—Li3	88.65 (18)	O4—Li2—B2 ⁱ	136.5 (2)
O6—B2—O4	121.2 (2)	$O4$ —Li2— $O1^{i}$	107.7 (2)
O6—B2—O5	121.6 (2)	O4—Li2—O2 ^{viii}	101.6 (2)
O6—B2—Li1 ^{viii}	40.79 (15)	O4—Li2—O5 ⁱ	108.5 (2)
O6—B2—Li2 ^v	137.1 (2)	O4—Li2—Li1 ^{xi}	87.7 (2)
O6—B2—Li3	37.74 (15)	O4—Li2—Li3 ^{xiii}	117.1 (2)
Li1 ^{viii} —B2—Li2 ^v	105.56 (17)	O5 ⁱ —Li2—Ga1 ^{iv}	31.06 (10)
Li1 ^{viii} —B2—Li3	70.99 (16)	O5 ⁱ —Li2—Ga1 ⁱ	74.16 (15)
Li3—B2—Li2 ^v	122.03 (17)	O5 ⁱ —Li2—Ga1 ^{vi}	127.9 (2)
Ga1—O1—Li2 ^v	109.59 (17)	O5 ⁱ —Li2—Ga1	125.0 (2)
B1—O1—Ga1	120.01 (17)	O5 ⁱ —Li2—B1 ^{viii}	140.4 (2)
B1—O1—Li2 ^v	129.9 (2)	$O5^{i}$ —Li2—B2 ⁱ	27.93 (10)
Ga1 ^v —O2—Li2 ^{viii}	109.59 (15)	O5 ⁱ —Li2—O2 ^{viii}	129.2 (3)
Ga1 ^v —O2—Li3 ^{ix}	103.87 (16)	O5 ⁱ —Li2—Li1 ^{xi}	44.44 (15)
B1—O2—Ga1 ^v	123.74 (16)	O5 ⁱ —Li2—Li3 ^{xiii}	90.06 (19)
B1—O2—Li2 ^{viii}	102.9 (2)	Li1 ^{xi} —Li2—Ga1 ^{vi}	121.89 (19)
B1—O2—Li3 ^{ix}	114.5 (2)	Li1 ^{xi} —Li2—Ga1 ⁱ	116.94 (18)
Li3 ^{ix} —O2—Li2 ^{viii}	99.6 (2)	Li1 ^{xi} —Li2—Ga1	119.78 (18)
B1—O3—Li1	120.6 (2)	Li1 ^{xi} —Li2—Ga1 ^{iv}	63.51 (13)
B1—O3—Li3 ^{vii}	133.1 (2)	Li1 ^{xi} —Li2—Li3 ^{xiii}	64.81 (16)
B1—O3—Li3 ⁱⁱ	110.7 (2)	Li3 ^{xiii} —Li2—Ga1 ^{iv}	120.57 (17)
Li1—O3—Li3 ⁱⁱ	108.2 (2)	Li3 ^{xiii} —Li2—Ga1 ^{vi}	57.29 (12)
Li1—O3—Li3 ^{vii}	95.7 (2)	Ga1 ^x —Li3—Li1 ⁱⁱ	63.82 (13)
Li3 ^{vii} —O3—Li3 ⁱⁱ	81.0 (2)	Ga1 ^x —Li3—Li2 ^{xiii}	62.79 (13)
Ga1—O4—Li2	112.52 (17)	B1 ⁱⁱ —Li3—Ga1 ^x	121.35 (18)
B2Ga1	127.86 (17)	B1 ⁱⁱ —Li3—B2	69.64 (14)
B2—O4—Li2	119.6 (2)	B1 ⁱⁱ —Li3—Li1 ⁱⁱ	57.56 (14)

Ga1 ⁱⁱ —O5—Li1 ^x	113.47 (16)	B1 ⁱⁱ —Li3—Li1 ^x	106.5 (2)
Ga1 ⁱⁱ —O5—Li2 ^v	115.56 (17)	B1 ⁱⁱ —Li3—Li1 ^{xi}	80.20 (17)
B2—O5—Ga1 ⁱⁱ	113.05 (16)	B1 ⁱⁱ —Li3—Li2 ^{xiii}	150.9 (2)
B2—O5—Li1 ^x	110.1 (2)	B2—Li3—Ga1 ^x	168.9 (2)
B2—O5—Li2 ^v	110.9 (2)	B2—Li3—Li1 ^x	60.43 (15)
Li2 ^v —O5—Li1 ^x	92.0 (2)	B2—Li3—Li1 ⁱⁱ	127.1 (2)
B2—O6—Li1 ^{viii}	112.8 (2)	B2—Li3—Li1 ^{xi}	64.26 (15)
B2—O6—Li1 ^{xi}	130.9 (2)	B2—Li3—Li2 ^{xiii}	108.51 (19)
B2—O6—Li3	117.0 (2)	O2 ^{xi} —Li3—Ga1 ^x	36.18 (10)
Li1 ^{xi} —O6—Li1 ^{viii}	83.6 (2)	O2 ^{xi} —Li3—B1 ⁱⁱ	122.9 (2)
Li3—O6—Li1 ^{xi}	95.2 (2)	$O2^{xi}$ —Li3—B2	141.0 (2)
Li3—O6—Li1 ^{viii}	112.6 (2)	$O2^{xi}$ —Li3—Li1 ⁱⁱ	77.94 (18)
B2 ^{viii} —Li1—Ga1 ⁱⁱⁱ	150.65 (19)	$O2^{xi}$ —Li3—Li1 ^x	130.1 (2)
B2 ^{viii} —Li1—Li2 ^{ix}	115.6 (2)	$O2^{xi}$ —Li3—Li1 ^{xi}	80.86 (19)
$B2^{viii}$ —Li1—Li3 ^{ix}	107.8 (2)	Ω^{2xi} Li3 Li2 ^{xiii}	41.01 (14)
$B2^{\text{viii}}$ Li1—Li3 ⁱⁱ	117.46 (19)	O^{2xi}_{ij} Li3 Li3 ^{xiv}	118.1 (3)
$B2^{\text{viii}}$ Li1—Li3 ^{vii}	81 65 (18)	$O3^{ii}$ —Li3—Ga1 ^x	97 47 (18)
$B2^{\text{viii}}$ Li1—Li3 ^{viii}	54 76 (14)	$O3^{x}$ —Li3—Ga1 ^x	73 34 (15)
O3-Li1-Ga1 ⁱⁱⁱ	90 74 (18)	$O3^{x}$ —Li3—B1 ⁱⁱ	1165(2)
$O3-Li1-B2^{viii}$	81 99 (18)	$O3^{ii}$ —Li3—B1 ⁱⁱ	27.27(10)
03 —Li1— 05^{vii}	110.1 (2)	$O3^{x}$ —Li3—B2	101.3(2)
$03-Li1-06^{viii}$	108.0(2)	$O3^{ii}$ —Li3—B2	92.9(2)
03 —Li1— 06^{ix}	117.7 (3)	$O3^{x}$ —Li3— $O2^{xi}$	103.3(2)
$O3-Li1-Li1^{xii}$	125 5 (3)	03^{ii} I i 3 02^{xi}	103.5(2) 112.5(2)
03—Li1—Li2 ^{ix}	153 3 (3)	03^{x} Li3 02^{ii}	990(2)
03—Li1—Li3 ^{vii}	42 42 (15)	$O3^{ii}$ I i3 I i1 ^x	1083(2)
03—Li1—Li3 ⁱⁱ	36.20(14)	$O3^{ii}$ I i3 I i1 ^{xi}	100.3(2) 103.2(2)
03—Li1—Li3 ^{viii}	133 3 (2)	$O3^{x}$ $Ii3$ $Ii1^{x}$	41 91 (14)
03—Li1—Li3 ^{ix}	75 85 (19)	$O3^{ii}$ I i3 I i1 ⁱⁱ	35 65 (13)
O5—LII—LIS $O5^{vii}$ —Li1—Ga1 ⁱⁱⁱ	31 78 (9)	$O3^{x}$ I $i3$ I $i1^{ii}$	99 1 (2)
$O5^{vii}$ _I i1_B2 ^{viii}	1262(2)	$O3^{x}$ I $i3$ I $i1^{xi}$	153.9(3)
O_{5}^{vii} I_{1}^{vii} I_{1}^{vii}	120.2(2) 124.5(3)	$\begin{array}{c} 03 \\ \hline \\ 03 \\ \hline \\ 13 \\ \hline \\ 12 \\ \hline \\ 12 \\ \hline \\ 12 \\ \hline \\ 11 \\ \hline \\ 12 \\ 12$	153.3(2)
$O5^{\text{vii}}$ Li1 Li2 ^{ix}	124.5(3)	$O3^{x} I i3 I i2^{xiii}$	133.3(2)
O_{5}^{vii} Li1 Li2 ^{viii}	45.00 (14) 86.42 (18)	$\begin{array}{c} \text{O3} & \text{E13} \\ \text{O3}^{\text{ii}} & \text{E3} \\ \text{I3}^{\text{ii}} & \text{I3} \\ \end{array}$	$J_{2.3}(2)$
$O5^{\text{vii}}$ Li1 Li3 ^{ix}	1260(2)	$O_3^{x} \text{Li3} \text{Li3}^{xiv}$	49.57 (18)
$O5^{vii}$ Li1 Li3 ⁱⁱ	82.63 (18)	$O_{5} - L_{13} - L_{13}$	$1/0^{2}$ (17)
$O5^{vii}$ Li1 Li3 ^{vii}	76 30 (19)	$O6 I3 B1^{ii}$	149.2(2) 82.26(18)
$O_{ix} = U_{i1} = C_{01}$	70.30(19)	$O_6 I_3 P_2$	32.20(18)
$O6^{\text{viii}}$ Li1 Galiii	140.8(2)	O_{0} L_{13} O_{2} D_{2}	23.20(10)
$O6^{\text{viii}}$ Li1 B2 ^{viii}	149.0(2) 26.37(10)	$06 \text{ Li}_{3} \text{ 03}^{\text{ii}}$	113.8(3) 109.1(2)
$O_{0} = D_{1} = D_{2}$	20.37(10) 112.2(2)	06 13 03	109.1(2)
O6 - LII - B2	113.2(2) 118.0(2)	06 Li3 Li1x	74.64(10)
$O_{0} = L_{1} = O_{0}$	116.0(2) 106.5(2)	O_{6} L_{13} L_{11}	/4.04 (19)
$O_{0} = L_{11} = O_{0}$	100.3(2)	O_{0} L_{13} L_{11}	+2.94(13)
$O_{0} = U_{1} = O_{0}$	30.4(2)	O_{0} L_{13} L_{11}	133.7(2)
$O_{0} = L_{11} = L_{11} =$	+0.01(17)	O_{0} L_{13} L_{12}	(2)
	+0.33(1/)	$U_{1} = U_{1} = U_{1$	120.2(3)
O_{0} $$ L_{11} $$ L_{12}	92.4 (<i>2</i>) 75.25 (19)	$L11^{}L13^{}Ua1^{-}$	112.15(18)
$U0^{-1}$ —L11—L12 ¹⁴	13.33 (18)	L11 —L13—Ga1 [*]	110.02 (19)

O6 ^{viii} —Li1—Li3 ^{vii}	103.7 (2)	Li1 ^x —Li3—Li1 ⁱⁱ	130.42 (19)
O6 ^{ix} —Li1—Li3 ⁱⁱ	106.1 (2)	Li1 ^{xi} —Li3—Li1 ^x	116.4 (2)
O6 ^{viii} —Li1—Li3 ⁱⁱ	143.8 (2)	Li1 ^{xi} —Li3—Li1 ⁱⁱ	106.95 (18)
$O6^{ix}$ —Li1—Li3 ^{vii}	155.5 (3)	Li1 ^x —Li3—Li2 ^{xiii}	96.3 (2)
$O6^{\text{viii}}$ _Li1_Li3 ^{ix}	109.5(2)	I_{i1}^{xi} I_{i3} I_{i2}^{xiii}	73.57(18)
O_{Cix} L_{11} L_{2ix}	109.5(2)		118.70(10)
	41.90 (13)	$L12^{m}$ $L13$ $L13$ $L11^{m}$	118.79 (19)
	96.9 (2)	L13 ^{AIV} —L13—Gal ^A	83.1 (2)
$O6^{vm}$ —L11—L1 3^{vm}	33.21 (13)	L_{13}^{xiv} — L_{13} — $B1^{ii}$	70.0 (2)
Li1 ^{xii} —Li1—Ga1 ⁱⁱⁱ	136.1 (3)	Li3 ^{xiv} —Li3—B2	100.9 (3)
$Li1^{xii}$ — $Li1$ — $B2^{viii}$	67.7 (2)	Li3 ^{xiv} —Li3—Li1 ^{xi}	150.0 (3)
Li1 ^{xii} —Li1—Li2 ^{ix}	81.0 (2)	Li3 ^{xiv} —Li3—Li1 ⁱⁱ	59.6 (2)
Li1 ^{xii} —Li1—Li3 ^{viii}	57.4 (2)	Li3 ^{xiv} —Li3—Li1 ^x	70.8 (2)
Li1 ^{xii} —Li1—Li3 ⁱⁱ	144.5 (3)	Li3 ^{xiv} —Li3—Li2 ^{xiii}	136.2 (3)
Ga1—O4—Li2—Ga1 ^{iv}	-102.80(13)	$06 - B^2 - 04 - Li^2$	0.4(4)
$Ga1 - 04 - Li2 - Ga1^{vi}$	66.9.(3)	06 B2 01 B2	-101.3(3)
	(0.5)(3)	$O(-D_2) = O(5 - Gar)$	101.5(5)
$Gal = O4 = Li2 = Oal^2$	-41.4(3)	$00-B2-05-L11^{2}$	20.8 (3)
$Gal = 04 = Li2 = Bl^{int}$	95.37 (14)	$06-B2-05-L12^{\circ}$	127.1 (3)
$Ga1 - O4 - L_{12} - B2^{1}$	-127.4(3)	L_1I^m —Gal—Ol—Bl	-37.0(2)
Gal—O4—Li2—O1 ¹	-12.7 (3)	Li1 ^m —Ga1—O1—Li2 ^v	135.94 (19)
Ga1—O4—Li2—O2 ^{viii}	95.0 (2)	Li1 ⁱⁱⁱ —Ga1—O4—B2	-105.3 (2)
Ga1—O4—Li2—O5 ⁱ	-126.46 (19)	Li1 ⁱⁱⁱ —Ga1—O4—Li2	72.3 (2)
Ga1—O4—Li2—Li1 ^{xi}	-166.36 (14)	Li1 ^{viii} —B2—O4—Ga1	-140.43 (17)
Ga1—O4—Li2—Li3 ^{xiii}	133.58 (18)	Li1 ^{viii} —B2—O4—Li2	42.1 (3)
B2-O4-Li2-Ga1 ^{iv}	75.0 (2)	Li1 ^{viii} —B2—O5—Ga1 ⁱⁱ	-149.04 (15)
$B2-O4-Li2-Ga1^{vi}$	-115.2(2)	$Li1^{viii}$ B2 O5 $Li1^{x}$	-21.0(3)
$B_{2}^{-} O_{4}^{-} I_{12}^{-} G_{2} I_{1}^{i}$	1364(2)	I_{i1}^{vii} B_{2}^{vii} O_{5}^{vii} I_{i2}^{vii}	793(3)
$\begin{array}{cccccccccccccccccccccccccccccccccccc$	177.8(3)	L_{11} L_{12} L_{12} L_{12} L_{11} L_{11} L_{11} L_{12} L	-101.9(3)
$D_2 = O_4 = L_{12} = O_{a1}$	26 9 (2)	$L_{11} = D_2 = O_0 = L_{11}$	101.9(3)
$B_2 = 04 = L_{12} = B_1^{-1}$	-80.8(2)	$L11^{}B2 - 00 - L13$	155.1(5)
$B2 - 04 - L12 - B2^{1}$	50.5 (4)	L12 ^{rt} —Ga1—O1—B1	/6./(2)
$B2 - O4 - L12 - O1^{1}$	165.1 (2)	L12 ^v —Ga1—O1—B1	-1/3.0(3)
$B2 - O4 - Li2 - O2^{viii}$	-87.2 (3)	Li2 ^{iv} —Ga1—O1—B1	-98.1 (2)
$B2-O4-Li2-O5^{i}$	51.4 (3)	Li2—Ga1—O1—B1	142.1 (2)
B2—O4—Li2—Li1 ^{xi}	11.5 (3)	Li2—Ga1—O1—Li2 ^v	-44.96 (17)
B2—O4—Li2—Li3 ^{xiii}	-48.6 (3)	Li2 ^{vi} —Ga1—O1—Li2 ^v	-110.28 (16)
O1—Ga1—O4—B2	42.2 (2)	Li2 ^{iv} —Ga1—O1—Li2 ^v	74.9 (2)
O1—Ga1—O4—Li2	-140.21(19)	Li2—Ga1—O4—B2	-177.6(3)
$O1 - B1 - O2 - Ga1^{v}$	-38.0(3)	$Li2^{iv}$ —Ga1—O4—B2	-80.7(2)
$\Omega_1 = B_1 = \Omega_2 = L_i 2^{\text{viii}}$	86 5 (3)	$Li2^{vi}$ —Ga1—O4—B2	130.6(2)
$01 - B1 - 02 - Li3^{ix}$	-1665(2)	$Li2^{v}$ —Ga1—O4—B2	330(2)
O1 P1 O2 Lis	-142.2(2)	Li2 Gal O4 $Li2$	55.0(2)
OI = DI = O3 = LII	143.3(3)	Li2 - Gal - O4 - Li2	50.9(2)
$OI = DI = O2 = L^2 2^{22}$	07.1 (5)	Li2 - Gal - O4 - Li2	-31.7(2)
$OI - BI - O3 - L13^{\text{vir}}$	-8.1(3)	L12	-149.4 (3)
O2 ⁱ —Ga1—O1—B1	48.3 (2)	L_{12} ^{win} —B1—O1—Ga1	-145.49 (15)
O2 ¹ —Ga1—O1—Li2 ^v	-138.71 (18)	$Li2^{vm}$ —B1—O1— $Li2^{v}$	43.1 (4)
$O2^{i}$ —Ga1—O4—B2	166.3 (2)	Li2 ^{viii} —B1—O2—Ga1 ^v	-124.5 (2)
O2 ⁱ —Ga1—O4—Li2	-16.1 (2)	Li2 ^{viii} —B1—O2—Li3 ^{ix}	107.0 (2)
O2—B1—O1—Ga1	165.44 (16)	Li2 ^{viii} —B1—O3—Li1	-14.5 (3)

O2-B1-O1-Li2 ^v	-5.9 (4)	Li2 ^{viii} —B1—O3—Li3 ^{vii}	120.7 (3)
O2—B1—O3—Li1	38.4 (4)	Li2 ^{viii} —B1—O3—Li3 ⁱⁱ	-142.1 (2)
O2—B1—O3—Li3 ⁱⁱ	-89.2 (3)	Li2 ^v —B2—O4—Ga1	-34.6 (2)
O2—B1—O3—Li3 ^{vii}	173.6 (3)	Li2 ^v —B2—O4—Li2	147.9 (3)
O3—B1—O1—Ga1	-13.0 (3)	Li2 ^v —B2—O5—Ga1 ⁱⁱ	131.7 (2)
O3—B1—O1—Li2 ^v	175.7 (3)	Li2 ^v —B2—O5—Li1 ^x	-100.3 (3)
O3—B1—O2—Ga1 ^v	140.4 (2)	Li2 ^v —B2—O6—Li1 ^{xi}	-151.7 (3)
O3—B1—O2—Li2 ^{viii}	-95.1 (3)	Li2 ^v —B2—O6—Li1 ^{viii}	-49.8 (4)
O3—B1—O2—Li3 ^{ix}	12.0 (3)	Li2 ^v —B2—O6—Li3	83.2 (4)
O4—Ga1—O1—B1	171.88 (18)	Li3 ^{vii} —Ga1—O1—B1	16.7 (2)
O4—Ga1—O1—Li2 ^v	-15.1 (2)	Li3 ^{vii} —Ga1—O1—Li2 ^v	-170.3 (2)
O4—B2—O5—Ga1 ⁱⁱ	80.4 (2)	Li3 ^{vii} —Ga1—O4—B2	162.9 (3)
O4—B2—O5—Li1 ^x	-151.6 (2)	Li3 ^{vii} —Ga1—O4—Li2	-19.4 (3)
O4—B2—O5—Li2 ^v	-51.3 (3)	Li3 ⁱⁱ —B1—O1—Ga1	33.9 (2)
O4—B2—O6—Li1 ^{viii}	78.0 (3)	Li3 ⁱⁱ —B1—O1—Li2 ^v	-137.4 (3)
O4—B2—O6—Li1 ^{xi}	-23.9 (4)	Li3 ⁱⁱ —B1—O2—Ga1 ^v	94.3 (2)
O4—B2—O6—Li3	-149.0 (3)	Li3 ⁱⁱ —B1—O2—Li2 ^{viii}	-141.2 (2)
O5 ⁱⁱ —Ga1—O1—B1	-70.85 (19)	Li3 ⁱⁱ —B1—O2—Li3 ^{ix}	-34.2 (3)
O5 ⁱⁱ —Ga1—O1—Li2 ^v	102.13 (18)	Li3 ⁱⁱ —B1—O3—Li1	127.6 (3)
O5 ⁱⁱ —Ga1—O4—B2	-69.7 (2)	Li3 ⁱⁱ —B1—O3—Li3 ^{vii}	-97.2 (3)
O5 ⁱⁱ —Ga1—O4—Li2	107.94 (19)	Li3—B2—O4—Ga1	139.9 (3)
O5—B2—O4—Ga1	-3.7 (3)	Li3—B2—O4—Li2	-37.5 (5)
O5—B2—O4—Li2	178.8 (2)	Li3—B2—O5—Ga1 ⁱⁱ	-81.93 (16)
O5—B2—O6—Li1 ^{viii}	-100.3 (3)	Li3—B2—O5—Li1 ^x	46.1 (2)
O5—B2—O6—Li1 ^{xi}	157.8 (3)	Li3—B2—O5—Li2 ^v	146.4 (2)
O5—B2—O6—Li3	32.7 (4)	Li3—B2—O6—Li1 ^{viii}	-133.1 (3)
O6—B2—O4—Ga1	177.91 (18)	Li3—B2—O6—Li1 ^{xi}	125.1 (4)

Symmetry codes: (i) x+1, y, z; (ii) -x+1, -y+1, -z+1; (iii) -x+1, -y, -z+2; (iv) -x+2, -y+1, -z+1; (v) x-1, y, z; (vi) -x+2, -y, -z+1; (vii) x, y-1, z+1; (viii) -x+1, -y, -z+1; (ix) x-1, y-1, z+1; (vi) x, y-1, z+1; (viii) -x+2, -y+1, -z+2; (xii) -x+2, -z+2; (xi) -x+2; (xi) -x+2;